Photo Album

by SORENSON, NATHANIEL M SA USAF AFOSI AFOSI/Det 814



You can't shake the taste of the blood



In a free society, you can own both.


















Cut the upright part to length and file or grind it to shape. File a slight bevel at the to rear of the upright.





Lightning Link

The parts for the Lightning Link can be made from tool steel, machined with great precision, hardened and tempered with loving care, the polished to a high gloss that your mother would be proud of. On the other hand, using only a couple of pieces of power hacksaw blade to make the parts from, a dremel tool, hand drill and one or two files to do the work, you can cut out the Lightning Link in about an hour.

The first description will make a link that you could most likely pass on to your great grandkids. The second may not last that long, but I know of one made from mild steel, that has never been hardened or tempered. It's been used to fire over 5,000 rounds, and still going strong. All that ever goes wrong with it is the part of the bolt carrier hits gets peened over after about five or six hundred rounds. When that happens, the woman that owns it drops it out of the gun, puts it on the rear bumper of her jeep and beats it back in shape with a rock. She's then back in business for a few hundred more rounds.

The only complaint I've ever heard about the Lightning Link is it converts the firearm to full auto only. I can't see that's a problem. No one says you have to hold the trigger down until the magazine's empty. I've found with a little practice it's easy to fire two shot bursts using the Link.


Also keep in mind; that it takes only about ten seconds to install the Lightning Link in a standard unaltered AR-15, and only about six seconds to remove it. Going from semi-auto to full and back to semi is only a matter of seconds.


How it works


In normal semi-auto operation the hammer is cocked by a rearward movement of the bolt carrier, as the carrier moves forward, the hammer is caught and held in the cocked position by the sear located on the forward part of the trigger catching in the sear notch, on the hammer. If you hold the trigger after a shot's fired the sear will not catch in the hammer's sear notch when the hammer cocks because the sear is depressed below the arc of the hammer notch.

What happens is because the trigger is being held back; the disconnector hook is tipped forward and in position to catch the hammer, stopping it from following the bolt carrier forward. When the trigger is released, it allows the hammer to slip from under the disconnector hook and be caught by the trigger sear in the hammer sear notch. Making it necessary to pull the trigger for each shot.

SCHEMATICS FOR FINISHING







Assembly

Refer to the first drawing. Install the parts in the lower receiver. See drawing [A]. Tip the weapon so the links upright rests against the rear of the receiver. Close the upper until the take-down pin post is far enough into the lower receiver, that when you tip the firearms muzzle down the links upright can rest against the post. Continue closing the weapon until it's completely closed. NOTE.... This first time you ma have trouble getting the link upright to slide in place between the rear of the takedown pin post and the bol carrier. All I can tell you is wiggle and jiggle things until it goes into place. It will fit in place much easier after its shaped by the bolt carrier.


After the takedown pin is in place, hold the trigger back and operate the bolt carrier about five times. The bolt carrier hitting it forms the bend in the top of the links upright at this time. See drawing [D]. Be sure to let the bolt slam with full force each time. Now's the time to find out if everything's working right. Cock th weapon, point it in a safe direction and pull the trigger. You should hear the hammer fall. Keep holding the trigger, cock the weapon, and release the trigger. Pull the trigger, nothing should happen, the Lightning Link will have released the hammer when the bolt carrier closed.


Test Fire

Load two rounds in the magazine. The first will fire when you pull the trigger, the second will fire automatically. Check the brass for any problems. If all's well, load five rounds and fire. If all goes well, load her up and let her rip.




IF YOU DON'T LIKE THE WAY THINGS WORK IN AMERICA...





When you think you ran over a dog but it's just a politician













Simpler over low begater about 5 min new

Remicion from freet, we consend expect

Slow Cooker Method

Add diricken, diricken stock, gentic union, dirits, oregano, carmi, chih powder, valt and pepper to a 5× quart alow cooker.


deck for \$ hours on low.

shred chicken with two forks and stir in white begand and fresh oregand and cook for an other to minutes.

Serve and enjoy!

What I appear to be doing.

What I'm actually doing.














waking you up in the middle of the night beating his wife.











"We can't do that, it's against the UCMJ"















When your Muslim neighbor keeps waking you up in the middle of the night beating his wife.



























Case 1:20-cr-01210-JCH Document 23-1 Filed 05/14/20 Page 29 of 44











Case 1:20-cr-01210-JCH Document 23-1 Filed 05/14/20 Page 31 of 44





Stearic acid (its a white solid)

Dried, powdered soap flakes (I hear ivory soap works well)

There are other things, but these are the most common and cheap Powdered sugar

Motor oil

liquid soaps (they contain water usually)

@free_rope_rides

You will want to get it thick enough to have a consistency like honey or syrup. Also remember to add sulfuric acid or sugar+potassium chlorate if you are using self igniting mixtures. Gas is cheap, test out your self igniting system before hand if you plan on using it.















free_rope_rides (I'm aware there are typos, deal with it) So key point is use the right thing to thicken the gas, (not oil or styrofoam). Always use a cap, don't stuff a rag in, use a self igniting method if you really want to get fancy, but rest it first to make sure it works. Gas is cheap, experiment a little to see what works best for you. Also don't do anything crazy, I just don't want anyone barbecuing themselves at the hoedown




(5) co 12 49 1 1 1 1

9










45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or







45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore.








Estes Sonic Igniters (4 Pack)

\$5.99 \$3.53



This is a great igniter for small composite motors that have small nozzles, like the D10, D21, E6, F10. It has thin wire and a small head, so it can reach up high into those motors. We recommend using this as a replacement for the copperhead igniter.

Wire Length = 10 inches Quantity per pack = 4 Maximum no-fire current = 1.25 A Minimum all-fire current = 3.80 A Igniter Resistance including lead wires = 1.6 ohms



45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.





Preparation

The preparation of HMTD always presents the risk of premature detonation and should not be attempted by amateurs. But if you really want to know:

14 g of hexamine is dissolved in 45 ml of hydrogen peroxide 30% concentration and stirred (mechanically) at 0 °C. An amount of 21 gram of finely powdered citric acid is then slowly added under continuous stirring for 3 h, at 0 °C. After 3 hours, the product is allowed to reach ro temperature and left for 2 h. The white crystalline product is filtered off, and washed thoroughly with water, to remove any water soluble impurit and rinsed with methanol. The wet product is air dried. This part is risky as the product may explode during drying. The yield is around 50-70%. Larger amounts are not safe to handle, so it's best to try to make smalls

Projects

amounts based on the process above.

Due to its instability, HMTD doesn't have many uses outside amateur explosives. As it is a stronger initiating explosive than mercury(II) fulminate, it can be used to make blasting caps, albeit they should be used quickly. Never use metal for these blasting caps, as this increases



45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.





Synthesis of Hexamethylene triperoxide diamine (HMTD)

With stirring, in a large beaker, 150 mL of 30% hydrogen peroxide is combined with 56 g of hexamine and 84 g of citric acid, the beaker is then immersed in an ice bath for 6h with occasional stirring. Then the mixture is filtered, washed with water and dried in air.

Source



45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.





TATP: a easily synthesized primary explosive.

- -very corrosive, allow NO contact with metal
- -can detonate even when wet so store it completely submerged in water if you must store it
- -deemed 'too unstable for commercial blasting caps' but is one of the main primaries used by "amateurs"
- -keeping any quantity past 2 grams at a time/in one place is extremely dangerous



45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.





Mix 50mL 30% hydrogen peroxide with 50mL acetone in a beaker. Put the breaker in an ice bath and cool to 8*C. Once cool, add 2.5-3mL concentrated (90%+) sulfuric acid drop wise as you stir constantly, make sure the temp doesn't go above 10*C. Leave the solution to cool in a fridge overnight. Filter the white precipitate though a coffee filter and rinse thoroughly with ice cold water/baking soda solution (to neutralize the acid). When dry it is an extremely powerful (and sensitive) primary explosive, capable of reliably setting off nearly all commercial explosives (except ANFO).



45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.






First synthesised in 1885 by Legler, [2] HMTD may be prepared by the reaction of an aqueous solution of hydrogen peroxide and hexamine in the presence of citric acid, acetic acid or dilute sulfuric acid as a catalyst. The hydrogen peroxide needs to be at least 12% w/w, lower concetrations lead to poor yields. Citric acid is overall superior to other acids. Common synthetic procedure uses 5 ml of 30% hydrogen peroxide, 2 g of citric acid and 1 g of hexamine with about 50% yields.





45 likes

free_rope_rides_2.0 Blasting cap tutorial, screenshot it. Plastic test tubes are the best container for caps to use since the base is seamless and safer. TATP and HMTD are both good for caps, be careful, they can be sensitive and can take hands/fingers off. Scale any recipes to yield no more than 3 grams, store wet, under water until ready to make caps. Don't do anything dumb or dangerous, know the laws of you choose to it ignore them that's up to you.











Dissolve 5 parts PARAFFIN wax and 5 parts Vaseline in the white gas. Pour this solution into 90 parts of your potassium chlorate (dry it right before mixing in an oven on low for about 20 mins). Mix this thoroughly and add 2-3% aluminum powder (2-3% of the weight of chlorate, wax and Vaseline, NOT the white gas). Spread this mixture out in a thin layer and let the white gas evaporate, this will be your final product.



.


 \square

A




This is a plastic explosive with a detonation velocity of around 3,300m/s and is comparable to 40% ammonia dynamite (c4 detonates at a little over 8,000m/s). This is not powerful enough for good shaped charges/EFPs, but is good for demo, claymores, grenades, etc. This should be formed into bricks and dipped in melted wax to water proof of you plan on storing it. These should detonate reliably with only a #3 (0.5-0.75g) blasting cap.






https://www.cia.gov/library/abbottabadcompound/6C/6C60F71F7 112A98B703E501FD2F924DF_ Chlotares From bleach and salt.doc.pdf








- them with <u>distilled water</u> in the following proportions: 56 G. per 100 ml. distilled water.
- · Heat this solution until it boils and allow it to cool.
- Filter the solution and save the crystals that form upon cooling.

These crystals should be relatively pure potassium chlorate.




4 likes

rope_rides_3 Just reposting to the backup so i won't loose it when My new main is zucced




(i) on 12 49 11 1

9



Case 1:20-cr-01210-JCH Document 23-1 Filed 05/14/20 Page 42 of 44





PLX was invented during World War II by the Picatinny Arsenal in New Jersey. It was originally designed to clear minefields by being spread via plane over the targeted area or poured from a safe distance and detonated by troops on the ground.

This explosive can also be gelled through the addition of nitrocellulose, ETN, or any number of soluble nitrate esters or gelling agents. This allows for powdered metals, such as aluminum or magnesium, to be suspended in the mixture. The metal powders act as fuel, increasing heat and energy output but lowering the brisance and VoD. The result is a more sustained blast wave and a "push and heave" effect, desirable for thermobaric purposes. Trzciński^[who7] reports that 200 grams of a mixture of NM with PMMA as gelling agent and AIMg (45:55, mean particle size = 63 microns) as fuel, in a ratio of 67:2/2.8/30 by mass, has a peak overpressure of 120 kPa 2 m from the(open air) blast site, a 1.65 TNT equivalency in peak pressure, and a 1.62 equivalency in shockwave impulse.^[1] This means that more than 50 % of eardrums will be perforated in case of 200 g PLX/magensium-aluminium alloy detonation at a distance of 2 m. 104 kPa is widely regarded as a pressure where 50 % of eardrums fail.^[2] It's still 3 - 5 less than needed to induce 50 % of fatalities via pulmonary injury as per Bass/Bowen equations (standing adult, facing any direction).^[3]

PLX has been implicated as one of the materials capable of being used in catastrophic terrorism, as most steel core columns can not withstand the detonation of 10 - 30 kg PLX in direct contact (explosive on bare steel). Nitromethane and its gelling agents are freely sold to the public in the US, though. Its sale to the public has been banned in the EU in september 2014. [4]




or any organization, go zucc something else IG

As usual, for educational purposes only, screenshot it while it's around and follow my backup @rope_rides_3

since it's just a matter of time till I'm deleted again

View all 20 comments





Lawmakers shouldn't get paid during the shutdown

We should get rid of all the non-essential government jobs

All government jobs are non-essential



"How dare you talk shit about cops like that. My brother died in the line of duty!"



